AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

- 1. (Currently Amended) An adhesive article comprising (a) a moisture resistant substrate having a first and second surface, and (b) a removable and resealable adhesive covering at least a first portion of the first surface of the substrate; wherein the removable adhesive is removable and resealable in the presence of moisture from refrigerated or frozen food packaging environments and has a Moist Loop Test result of at least about [[0.25]] <u>0.8</u> N/25mm at a test plate temperature of 5°C.
- 2. (Original) The article of claim 1 wherein the moisture resistant substrate comprises a polymer coated paper facestock.
- 3. (Original) The article of claim 1 wherein the moisture resistant substrate comprises a monolayer or multilayer polymeric film.
- 4. (Original) The article of claim 1 wherein the substrate comprises a multilayer film.
- 5. (Original) The article of claim 1 wherein the substrate comprises a film selected from polystyrenes, polyolefins, polyamides, polyesters, polycarbonates, polyurethanes, polyacrylates, polyvinyl alcohol, poly(ethylene vinyl alcohol), poly(alkylene vinyl acetates), poly(alkylene acrylates), ionomers, and mixtures thereof.
- 6. (Original) The article of claim 1 wherein the substrate comprises a polyolefin film.

- 7. (Original) The article of claim 1 wherein the substrate comprises an ethylene or propylene polymer or copolymer.
- 8. (Currently Amended) The article of claim 1 wherein the removable adhesive comprises an acrylic based or rubber based pressure sensitive adhesive.
- 9. (Currently Amended) The article of claim 1 wherein the removable adhesive has a Moist Loop Test result of at least about 0.28 N/25mm at a test plate temperature of 5°C comprises a UV curable hot melt acrylic adhesive.
- 10. (Original) The article of claim 1 where the removable adhesive comprises a hot melt pressure sensitive adhesive.
- 11. (Original) The article of claim 1 wherein the removable adhesive comprises a rubber based adhesive.

12-17 (Cancelled)

- 18. (Original) The article of claim 1 further comprising (c) at least one permanent adhesive covering a second portion of the first surface of the substrate.
- 19. (Currently Amended) The article of claim 18 wherein the removable permanent adhesive comprises a rubber based adhesive, an acrylic adhesive, a vinyl ether adhesive, a silicone adhesive, or mixtures of two or more thereof.
- 20. (Original) The article of claim 18 wherein the permanent adhesive comprises an acrylic based or rubber based pressure sensitive adhesive.

21-40 (Cancelled)

41. (Currently Amended) A sheet of adhesive closures comprising: a carrier sheet having a release surface; and

a plurality of adhesive articles releasably adhered to the release surface of the sheet, each article comprising (a) a moisture resistant substrate having a first and second surface, and (b) a removable and resealable adhesive covering at least a first portion of the first surface of the substrate; wherein the removable adhesive is removable and resealable in the presence of moisture from refrigerated or frozen food packaging environments and has a Moist Loop Test result of at least about [[0.25]] 0.8 N/25mm at a test plate temperature of 5°C.

- 42. (Original) The sheet of claim 41 wherein the adhesive article further comprises (c) at least one permanent adhesive covering a second portion of the first surface of the substrate.
 - 43. (Currently Amended) A roll of adhesive closures comprising: a wound carrier having a release surface; and

a plurality of adhesive articles releasably adhered to the release surface of wound carrier, each article comprising (a) a moisture resistant substrate having a first and second surface, and (b) a removable and resealable adhesive covering at least a first portion of the first surface of the substrate; wherein the removable adhesive is removable and resealable in the presence of moisture from refrigerated or frozen food packaging environments and has a Moist Loop Test result of at least about [[0.25]] 0.8 N/25mm at a test plate temperature of 5°C.

44. (Original) The roll of claim 43 wherein the adhesive article further comprises (c) at least one permanent adhesive covering a second portion of the first surface of the substrate.

45. (New) The adhesive article of claim 1 wherein the removable and resealable adhesive is removable and resealable at temperatures within the range of from about 10°C to about -30°C.